

KODAK Premium Rapid-Dry Photographic Papers / 260g



KODAK Premium Rapid-Dry Photographic Glossy Paper / 260g

KODAK Premium Rapid-Dry Photographic Lustre Paper / 260g

GENERAL DESCRIPTION

Premium Rapid-Dry Photographic Paper / 260g offers the ideal weight, thickness and finish for high quality photographic reproductions. With superb color image quality, guaranteed performance for longevity, universal compatibility with piezo and pigment systems, and the power of the KODAK brand behind it, this media is ready made for the professional photographer.

- Bright clean, low DMIN provides excellent whites, highlight detail and contrast
- Performance Guaranteed up to 150 years indoors
- Lustre surface identical to Kodak range of photographic paper E surface, such as ENDURA, to match prints
- Lustre surface provides superb uniformity of gloss from highlights to shadows

COMPATIBILITY

When used with the following printers and inks, KODAK Premium Rapid-Dry Photographic Papers are recommended for all applications if laminated/overcoated. Recommendations will provide optimal output when using printing paths commonly associated with each printer. These settings are intended as starting points—other combinations of settings may also provide good results. See "Printing Notes" for more information. "Yes" in the Laminate Recommendation column indicates that this media is likely to have good adhesion with laminates in that class.

For compatibility information for all KODAK Wide-Format Inkjet Media, refer to the Inkjet Media Compatibility Chart at www.kodak.com/go/wideformat.

Manufacturer	Model	Ink Compatibility		Laminate Recommendation (See Finishing Section)			
		Ink	Print Driver Media Setting	Heat Activated Thermal* 210-240°F (99-116°C)	Heat Activated Low Temperature* 185-195°F (85-91°C)	Heat Assisted 185-195°F (85-91°C)	Pressure Sensitive† Ambient to 120°F (49°C)
HEWLETT-PACKARD DESIGNJET	2000/2500/2800/3000/3500/3800 CP	Dye‡	See Printing Notes	Yes	Yes	Yes	Yes
HEWLETT-PACKARD DESIGNJET	2000/2500/2800/3000/3500/3800 CP	UV	See Printing Notes	Yes	Yes	Yes	Yes
HEWLETT-PACKARD DESIGNJET	5000 Series	Dye‡	Productivity Photo Gloss	Yes	Yes	Yes	Yes
HEWLETT-PACKARD DESIGNJET	5000 Series	UV ^{II}	Productivity Photo Gloss	Yes	Yes	Yes	Yes
HEWLETT-PACKARD DESIGNJET	Z Series	VIVERA Pigments	HP Premium Instant-Dry Photo Gloss	Yes	Yes	Yes	Yes
ENCAD NOVAJET	600/700 Series	GS‡, GS+‡, GX‡	See Printing Notes	Yes	Yes	Yes	Yes
ENCAD NOVAJET	800 Series	GS+‡, GX‡	See Printing Notes	Yes	Yes	Yes	Yes
ENCAD NOVAJET/ KODAK	1000i/1200i	Qi Dye‡	See Printing Notes; Printer Heater Setting: 2	Yes	Yes	Yes	Yes
ENCAD NOVAJET/ KODAK	1000i/1200i	Qi Pigment ^{II}	See Printing Notes; Printer Heater Setting: 2	Yes	Yes	Yes	Yes

Continued Next Page

©Eastman Kodak Company, 2008



Manufacturer	Model	Ink Compatibility		Laminate Recommendation (See Finishing Section)			
		Ink	Print Driver Media Setting	Heat Activated Thermal* 210-240°F (99-116°C)	Heat Activated Low Temperature* 185-195°F (85-91°C)	Heat Assisted 185-195°F (85-91°C)	Pressure Sensitive† Ambient to 120°F (49°C)
CANON	7250D/7200D/ 8200D/8400D	Dye	Photo Glossy Paper	Yes	Yes	Yes	Yes
CANON	6200Pg/8200Pg 6400Pg/8400Pg	Pigment	Photo Glossy Paper	Yes	Yes	Yes	Yes
CANON	iPF9000/ iPF8000/ iPF5000	LUCIA Pigments	Photo Glossy Paper/ Cassette: Photo Paper Plus Semi-Gloss	Yes	Yes	Yes	Yes
ROLAND HI-FI JET	Hi-Fi Jet FJ-50/ FJ-40, Hi-Fi Jet Pro FJ-400/FJ-500/FJ-600	Dye‡§	See Printing Notes	Yes	Yes	Yes	Yes
ROLAND HI-FI JET	Hi-Fi Jet FJ-50/ FJ-40, Hi-Fi Jet Pro FJ-400/FJ-500/FJ-600	Pigments	See Printing Notes	Yes	Yes	Yes	Yes
EPSON STYLUS PRO	R2400	ULTRACHROME K3	Premium Luster Photo Paper/Best Photo or Photo RPM Print Mode	Yes	Yes	Yes	Yes
EPSON STYLUS PRO	R1800	ULTRACHROME HI-GLOSS	Premium Luster Photo Paper/Best Photo or Photo RPM Print Mode	Yes	Yes	Yes	Yes
EPSON STYLUS PRO	7000/9000 Series	Dye‡	Photo Quality Inkjet Paper	Yes	Yes	Yes	Yes
EPSON STYLUS PRO	10000 Series	Photographic Dye‡	Photo Glossy Paper	Yes	Yes	Yes	Yes
EPSON STYLUS PRO	7500/9500	Pigment	Premium Luster Photo Paper	Yes	Yes	Yes	Yes
EPSON STYLUS PRO	4000 Series	ULTRACHROME Pigment	Premium Luster Photo Paper	Yes	Yes	Yes	Yes
EPSON STYLUS PRO	7600/9600/ 10600	ULTRACHROME	Photo Glossy Paper	Yes	Yes	Yes	Yes
EPSON STYLUS PRO	10000 Series	ARCHIVAL	Photo Glossy Paper	Yes	Yes	Yes	Yes
EPSON STYLUS PRO	3800/4800/7800/9800 4880/7880/9880/11880	ULTRACHROME K3	Premium Luster Photo Paper	Yes	Yes	Yes	Yes

* Imaging-side lamination is not recommended for heat-activated laminates thicker than 3 mils, when printing with pigment-based inks. Additional total thickness and rigidity can be achieved by using thicker laminates on the non-imaging side.

† Do not use pressure-sensitive laminates with solvent-based adhesives.

‡ For optimal durability, laminate soon after printing (within 4 hours).

§ Based on our testing experience and knowledge of these Printer / Ink combinations, we expect that KODAK Rapid-Dry Photographic Papers are compatible, although they have not been extensively tested.

¶ Images and graphics printed on these printers with pure black (K) ink only are more susceptible to smudging than those printed with a combination of inks (process black). Adjust images and/or output profiles to replace pure K with process black to increase the physical durability of the print.

Note: Premium Rapid-Dry Photographic Papers are not recommended for use with dye inks unless laminated. To extend the print lifetime, laminate within 4 hours of printing to protect from exposure to air. See Finishing section for additional details.

PRINTING NOTES

The print driver media settings recommended in the Compatibility section are intended to provide usable results with available media profiles found in the printer manufacturer's provided drivers and RIPs. These recommendations will provide proper ink laydowns with no pooling or bleeding, and color which will be acceptable for many applications. It is suggested that tests be run using these recommendations and color corrections be made to meet user expectations.

In cases where no recommendation is made, choose the media setting closest to the KODAK Wide-Format Inkjet Media you are using. This should give you a print which requires little or no adjustment to get usable results.

Kodak does not recommend using Premium Rapid-Dry Photographic Paper with the HP PHOTOSMART PRO B9180 Printer.

RIPs and Profiles for ENCAD and Other Printers

For more exacting color, several third party RIPs (Raster Image Processors) are available with profiles supporting KODAK Media for ENCAD, KODAK and other printers. For more information visit KODAK's website at www.kodak.com/go/wfipfiles

Following is a list of RIPs for which ENCAD/KODAK printer support and Kodak-built media profiles are available:

ENCAD/KODAK	www.encad.com/Support/RIP-Support/index.asp
COLORGATE PHOTO RIP	www.colorgate.com/home_e/products_e.html
ONYX GRAPHICS	www.onyxgfx.com
SCANVEC AMIABLE	www.scanvecamiable.com

In addition to the above list, the following software companies provide RIPs and profiles that support ENCAD/KODAK printers:

BEST GMBH	www.bestcolor.com/bcint/index.htm
AIT INTERNATIONAL	www.applied-image.com/Shiraz-RIP.htm
IMAGE TECHNOLOGIES	www.imagetechdev.com
GLOBAL GRAPHICS	www.globalgraphics.com
COLORBURST SYSTEMS	www.compatsys.com
WASATCH COMPUTER TECHNOLOGY, INC.	www.wasatchinc.com
CADLINK TECHNOLOGY	www.cadlink.com
JET RIP	www.jangeun.co.kr

Custom Profiles

While the above printing recommendations and available profiles from Kodak will provide adequate results for many wide-format inkjet applications, there are applications, such as inkjet proofing, which demand more exacting color requirements. It is suggested that for these applications, custom profiles be built for given ink/media/printer combinations. Many color management and profile building software applications are available which allow the user to manage color to meet their needs. Also, many RIPs will provide color profiling options which allow the user to control the color of their output. Please contact your dealer or KODAK Technical Support for help determining the best solution for your application.

Matte Black Inks

Matte Black inks, intended to be used with coated and fine art papers, are not compatible with porous photographic papers, never drying and easily smudged from the paper's surface. Check with your printer and ink manufacturer for complete details on the proper usage of this type of ink.

HANDLING

All inkjet media must be handled with care before and after printing to prevent damage to the ink receiving layer and printed images. Use the following guidelines, your experience, and common sense for the proper care of your media.

- Store unused media in its original packaging, using the core-plugs and plastic sleeves.
- Allow media to acclimate to your environmental conditions for at least 24 hours before use.
- KODAK Inkjet Media is rolled printable side out. Avoid touching the printable side by handling by the edges of the roll.
- Wear cotton gloves when handling media to avoid scratches, abrasions and fingerprints from moisture and oils on your hands.
- Do not allow the media to come into contact with moisture. Moisture will damage many types of inkjet medias before and after printing.
- Avoid handling, trimming, laminating or other finishing until prints are completely dry. Dry times will vary based on media type, ink type and environmental conditions.
- Do not fold, bend or crease media or damage may occur to the ink receiving layer.
- Do not allow the surface of the media to come into contact with itself or another inkjet media.
- Use media only in recommended operating conditions—see "Physical Characteristics" section.

Curl

Most types of roll-based inkjet media will exhibit some amount of curl, either toward the base side or toward the print side. This will vary based on media type and environmental conditions. Some media will curl more in low humidity environments and others in high humidity environments. Also, media may curl more towards the core or end of the roll due to "roll memory."

Although curl is mainly an issue when printing, it can also have an impact on laminating and other finishing procedures. Follow these guidelines, and use your experience and common sense to avoid issues caused by curl.

When printing:

- Advance media several inches past the print platen before starting a print job.
- Add weights or clips to the leading edge of the media.
- Attach media to the printer's take-up spool before starting printing.
- Adjust vacuum settings accordingly on printers equipped with variable media vacuum settings.
- Adjust heater and dryer settings on equipped printers to obtain optimum conditions to ensure flat media.

See printer owners' manual for their recommendations.

During finishing:

- Reverse wind media, when completely dry, to counteract roll memory.
- Do not allow media to remain rolled for extended periods of time.
- Rough cut prints and lay them flat before laminating.

FINISHING

Detailed information and tips can be found in KODAK publication E-2600, *Laminating, Mounting, and Finishing KODAK Wide-Format Inkjet Media*.

Lamination

Please refer to lamination chart in compatibility sections above for specific printer/ink/laminate recommendations.

Lamination Definitions

Heat Activated Thermal, 210-240°F (99-116°C)*	Polyester laminates applied with hot roll laminators at 210-240°F.
Heat Activated Low Temperature, 185-195°F (85-91°C)*	Polyester laminates applied with hot roll laminators at 185-195°F.
Heat Assisted, 185-195°F (85-91°C)	Polyester or vinyl laminates with pressure sensitive adhesives; specially formulated for inkjet prints, and applied with hot roll laminators at 185-195°F.
Pressure Sensitive, Ambient to 120°F (49°C)	Polyester or vinyl laminates with pressure sensitive adhesives on a release liner, applied at ambient conditions or at low temperature, 100-120°F.

* For both Heat Activated Thermal and Low Temperature, use a laminate with a total thickness (polyester and adhesive) of 3 mils or less on the face side. Thicker laminates may be applied to the back of the print for increased total thickness.

Prints must be laminated prior to display to ensure optimum performance and guard against dye fade due to environmental pollutants.

Successful lamination requires that inkjet media be completely dry to ensure good adhesion and to avoid unwanted color shifts. While prints may feel dry to the touch, components of the ink that prevent good adhesion or may cause the color to change may still be present. The best drying is achieved while prints are exposed to air, not stacked or on a roll. For best results, use inkjet-specific laminate products.

For increased durability, choose a laminate with UV protection and encapsulate with a 1/4-1/2" (6.5-13 mm) seal around the edges of a print to prevent moisture and other airborne pollutants from reaching the image. Heavier weight papers may require a wider edge seal.

Mounting

Prints can be mounted, laminated or not, to a variety of materials, including poster board, foam board, SINTRA, LEXAN and more. Use inkjet-specific adhesive materials and follow the manufacturer's instructions.

DISPLAY

KODAK Inkjet Media is intended for display in typical home, office, and retail environments. Unusual conditions, such as extreme temperatures or humidity, may affect the expected lifetime of the displayed print. Kodak is unable to test all possible environments, so it is recommended to test display conditions when possible to be sure that the media meets the necessary requirements

PERFORMANCE GUARANTEE

Kodak will guarantee prints from compatible systems against noticeable fading, cracking, yellowing, and bleeding when the print is viewed from its intended viewing distance.

The Indoor Performance Guarantee durations will vary based on the media/printer/ink system. The stated durations assume the media is displayed indoors under fluorescent light (average intensity 450-lux, 12 hours/day), and/or with indirect sunlight exposure (at least 6 feet from a window, with no direct sunlight). The guarantee covers both laminated or unlaminated prints as noted in the table below. The unlaminated guarantee assumes the media will be displayed in a typical office environment and will not be exposed to a high level of pollutants (above a typical ozone level for an office environment).

Terms, conditions and additional information about the Performance Guarantee can be found at:
www.kodak.com/go/wideformat

Manufacturer	Model	Ink	Durability
HEWLETT-PACKARD DESIGNJET	5000 Series	6 Color Dye	2 years laminated
		6 Color UV	32 years 150 years laminated
	2xxx/3xxx	4 Color Dye	3 years laminated
		4 Color UV	32 years 150 years laminated
	Z2100/Z6100	8 Color VIVERA Pigments	50 years 150 years laminated
	Z3100	12 Color VIVERA Pigments	40 years 150 years laminated
ENCAD NOVAJET	800, 700, 600, 500 Series	4/8 Color GS+	6 months laminated
		4/8 Color GX	2.5 years laminated
ENCAD NOVAJET/ KODAK	1000i/ 1200i	Qi Dye	5 years laminated
		Qi Pigment	35 years 150 years laminated
EPSON STYLUS PRO	7000/9000	6 Color Dye	1 year laminated
	7600/9600/10000/10600	6 Color Photographic Dye	1 year laminated
	9500	6 Color Pigment	35 years 150 years laminated
	10000/10600	6 Color ARCHIVAL Pigment	35 years 150 years laminated
	4000/7600/9600/10600	6 Color ULTRACHROME	35 years 150 years laminated
	3800/4800/7800/9800	8 Color ULTRACHROME K3	35 years 150 years laminated
	7880/9880/11880	8 Color ULTRACHROME K3	Testing In Progress
EPSON STYLUS PHOTO	R2400	8 Color ULTRACHROME K3	35 years 150 years laminated
	R1800	8 Color ULTRACHROME Hi-Gloss	35 Years Unlaminated
CANON	7250D/7200D/8200D/8400D	6 Color Dye	3 years laminated
	6200Pg/8200Pg	6 Color Pigment	150 years laminated
	6400Pg/8400Pg	6 Color Pigment	20 years 150 years laminated
	iPF5000/iPF8000/iPF9000	12 Color LUCIA Pigments	35 Years 150 years laminated

Additional Durability Information

The following table can be used as a guide for printers and inks not included in the Performance Guarantee.

Durability Guidelines for Printers Not Included in Performance Guarantee

If Using	Expect Durability Similar To:
COLORSPAN EC	ENCAD GX
ROLAND Dye	EPSON 9000 Dye
ROLAND Pigment	EPSON 9500 Pigment

ORDERING INFORMATION

KODAK Premium Rapid-Dry Photographic Glossy Paper / 260g

Roll Length	Roll Width / Order No.					
	17 in. (43.2 cm) 3-inch core	24 in. (61 cm) 2-inch core	36 in. (91.4 cm) 2-inch core	42 in. (106.7 cm) 2-inch core	50 in. (127 cm) 2-inch core	60 in. (152.4 cm) 2-inch core
100 ft (30.5 m)	1714344	1539832	8989212	8407991	NA	NA
16.4 ft (5 m) (sample)	NA	8900789	NA	NA	NA	NA

Sheet Size / Order No.	
8.5 x 11 in. (216 x 279 mm) 50 Sheets	13 x 19 in. (330 x 483 mm) 20 Sheets
8720088	1216274

KODAK Premium Rapid-Dry Photographic Lustre Paper / 260g

Roll Length	Roll Width / Order No.					
	17 in. (43.2 cm) 3-inch core	24 in. (61 cm) 2-inch core	36 in. (91.4 cm) 2-inch core	42 in. (106.7 cm) 2-inch core	50 in. (127 cm) 2-inch core	60 in. (152.4 cm) 2-inch core
100 ft (30.5 m)	8701518	8512899	8201402	8929515	NA	NA
16.4 ft (5 m) (sample)	NA	1604123	NA	NA	NA	NA

Sheet Size / Order No.	
8.5 x 11 in. (216 x 279 mm) 50 Sheets	13 x 19 in. (330 x 483 mm) 20 Sheets
8465742	1598689

NA = Not available

PHYSICAL CHARACTERISTICS

Physical Characteristics	Glossy / 260 g	Lustre / 260 g	Test Method Reference
Caliper	9 mil (229µm)		ISO 534
Opacity	>95		Tappi T 524
CIE Whiteness	122		Tappi T 524
Weight	260 g/sm		ISO 536
Brightness	101		Tappi T 524
60-degree Gloss	60	25	ISO 7668
L*(D65/10 uvi/BBW)	96		Tappi T 524
Flame Spread Classification	Class A		ASTM E84
Operating Conditions	59-86°F (15-30°C), 30-70% RH (non-condensing)		
Recommended Storage Conditions	68°F (20°C), 50% RH		

Family of KODAK Photo and Fine Art Media

KODAK Premium Rapid-Dry Photographic Glossy Paper, 260g

KODAK Premium Rapid-Dry Photographic Lustre Paper, 260g

KODAK Fine Art Smooth Paper / M315DP

KODAK Fine Art Textured Paper / M315DP

KODAK Fine Art Fibre Satin Paper / SM285DP

KODAK Fine Art Fibre Glossy Paper / GL285DP

KODAK Fine Art Coated Matte Paper / M200DP

KODAK Artists' Semigloss Canvas / 20mil

KODAK Matte Canvas / 19mil

If you have questions or need assistance, visit Kodak's website at www.kodak.com/go/wfisupport or, in the U.S., contact KODAK Technical Support at 1-888-436-2347.

The contents of this publication are subject to change without notice.

EASTMAN KODAK COMPANY • ROCHESTER, NY 14650

Kodak

KODAK Premium Rapid-Dry
Photographic Papers / 260g
KODAK Publication No. E2635

KODAK is a trademark of the Eastman Kodak Company

March, 2008



 (+34) 968 722 350

 arkipLOT@arkipLOT.com